

**Client:** Stage Electrics Partnerships Ltd  
Encore House, Unit 3 Britannia Rd,  
Patchway Trading Estate, Patchway  
Bristol  
BS34 5TA

**Entry No:** 65387-01

**Date received:** 03/06/2014

**Client's Description:** 100% Polyester Curtain

**TEST REPORT**

**Test Required:** Flammability BS 5867-2 : Type B  
**Pre-treatment:** None  
**Conditioning:** A minimum of 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 2°C  
**Method of Test:** BS EN ISO 15025 : 2002 Procedure A (surface ignition)  
**Date of Test:** 19/06/2014

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

**Flame application time 15 seconds using propane gas**


Tested on face	Fabric length direction			Fabric width direction		
Specimen number	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge (✓ or X)	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X	X	X
Tested on Back	Fabric length direction			Fabric width direction		
Specimen number	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge (✓ or X)	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X	X	X

**Comments**

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



Geoff Briggs C. Text., A.T.I.  
Head of laboratory  
25<sup>th</sup> June 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



**Client:** Stage Electrics Partnerships Ltd  
Third Way  
Avonmouth  
Bristol  
BS11 9YL

**Entry No:** 65387-01

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2 : 2008. **In accordance with the requirements of BS 5867 the fabric should be labelled "IF WETTED IN ANY WAY IT IS ESSENTIAL TO RE-TREAT THE FABRIC TO MEET FLAMMABILITY REQUIREMENTS"**

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



Geoff Briggs C.Text., A.T.I.  
Head of laboratory  
25<sup>th</sup> June 2014



1104

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

